


A SURTECO BRAND

Technical Datasheet - Döllken melamine edgebands

Characteristics: Döllken Softforming edgebands are continuous single

layer edgebands off a roll with finish surfaces. Manufactured using lightfast special paper printed in plain colours and impregnated with duroplastic resins.



Type: Radii from 3 mm

■ Thickness: 0.28 – 0.31 mm



Areas of application: Softforming profiles

Base material: • Chipboards

MDF boardsSolid wood

etc.

Processing: Döllken Softforming edgebands can in principle be processed on all Softforming

edgeband machines. Depending on the edgeband profile, the machine temperature, forming path, hot air blower and adhesive system will need to be accurately adjusted.

Example: EVA hot melt adhesive wood moisture: ca. 8 - 12% Processing temperature at the roller: ca. 190 - 210°C Feed rate: ca. 20 m/min

Please heed the machine and adhesive supplier specifications. The temperature of the processed material should not be below 20°C.

Embossing: • Bead texture

Finish varnishing

Clear varnish: • Good chemical and mechanical resistance

Limited stability around pores if used as actual pore filler

Not coatable

Surface

characteristics: Chemical Stress Group DIN 68861, Part 1B to 1D

Lightfastness: At least 6 on the International Wool Scale, DIN EN ISO 105-B02



A SURTECO BRAND

Underside preparation: Roughened:

For special processing methods (e.g. PVAc gluing)

PVAc glue:

Pre-coating of the edgebands for processing by thermal activation

Bonding agent:

Polyurethane bonding agent for reliable gluing of our products with e.g. Polyamide hot melt adhesive, urea and other gluing systems.

HSK coating:

• EVA hot melt adhesive (normal and special heat

resistance)

• Polyamide hot melt adhesive for the industrial, technical and do-it-

yourself.

Form of delivery: • 23 x 0.3 mm

- 33 x 0.3 mm

Hot melt adhesive coating: optional

Roll inner core diameter: 150 mmRoll length with adhesive: 50 r.m.

Roll length without

adhesive: 100 r.m.

Packaging: LDPE packaging bag

Storage: At least 6 months in cool and dry places in original packaging (ca. 20°C, 55 - 56%

humidity).

Information provided in this Datasheet is based on practical experience and on the results of own testing and our current knowledge. It is intended exclusively to serve as information and does not imply any warranty, assurance of specific product characteristics or suitability for specific purposes.

Since we have no influence over materials and processing conditions we accept no liability whatsoever.

Our General Terms of Sale or, for cross-border business, our International Terms of Sale for customers outside Germany, shall always and exclusively apply to the legal relationship with our customers; these terms may be viewed on our website www.bauschlinnemann.de, as amended, and may be sent to you on request. We shall not be bound by customers' conflicting or deviating terms and conditions.

Date: 27.08.15

Further information:

Döllken-Kunststoffverarbeitung GmbH Beisenstr. 50 · 45964 Gladbeck · Germany Phone: +49 2043 979-0 · Fax: +49 2043 979-630

info@doellken.com www.doellken-kv.com